

# ROMANZA

thickness: 1.0-1.2MM  
average size: 53 sq. ft  
availability: In Stock  
category: Semi-Aniline  
finish type: Antique  
raw material: European  
Made in Italy

Romanza is semi aniline, hand antiqued leather which provides any piece with a sophisticated yet oh so comfortable look. Romanza has been hand stained with a combination of subtle oils and waxes, followed by a protective topcoat to give it excellent wear ability. It is then hot ironed to give it an added finish and a see through look reminiscent of the old English Bridle leathers. Once upholstered, the beauty and workmanship of this leather is amplified and brought to life.

**Colorways available:** Black, Caramel, Chivas, Chocolate, Cinnamon, Citron, Deep Sea, Gunmetal, Harness Brown, Midnight, Oak, Peacock, Sage, Sand, Smoke, Spice, Walnut and Whiskey

## SPECIFICATIONS

### performance characteristics

### PERFORMANCE LEATHER

<b>EN ISO 4045</b>	
DETERMINE Ph & Ph (DIFFERENCE FIGURE)	Min 3,2
<b>ISO105/B02</b>	
COLOR FASTNESS OF LEATHER TO LIGHT: XENON LAMP	Grey Scale ≥ 3 on specimen Grey Scale = 3 on Reference Blue Wool #4
<b>EN ISO 15700</b>	
COLOR FASTNESS TO WATER SPOTTING	Grey Scale ≥ 3 (No permanent swelling)
<b>ISO 11641</b>	
COLOR FASTNESS OF LEATHER TO PERSPIRATION	80 Cycles ≥ 3.5
<b>EN ISO 11640</b>	
COLOR FASTNESS OF LEATHER TO RUBBING	500 Cycles Dry ≥ 4 250 Cycles Wet ≥ 3.5
<b>EN ISO 11644</b>	
FINISH ADHESION	3 N/cm
<b>EN ISO 3376</b>	
MEASURE TENSILE STRENGTH AND % ELONGATION	Tensile Strength ≥ 8 Mpa % Elongation ≤ 80%
<b>EN ISO 5402</b>	
FLEXING ENDURANCE (FLEXOMETER METHOD)	50,000 Cycles (no finish damage cracks)
<b>EN ISO 17233</b>	
COLD CRACK RESISTANCE OF FINISH	-15°C (no finish cracks)
<b>EN ISO 3377-1</b>	
TEAR STRENGTH (SINGLE EDGE TEAR)	>20 N Minimum

### flame resistance

CA TB 117 - 2013	Complies
NFPA - 260 CIGARETTE IGNITION	Class 1
FMVSS 302	Complies

